

IN THE SPECIFICATION:

Amend lines 16-17 at page 10 of the specification to read as follows:

The penetration of the wax is measured according to JIS K 2235-5.4. "Penetration" is a measure of hardness of petroleum asphalt or petroleum wax. It indicates ten times distance (mm) by which a needle under a load of 100g vertically penetrates a sample whose temperature is maintained at 25°C in 5 seconds. The greater the value of penetration, the softer the sample.